

PVC 100 Hartschaum



Dichte kg/m ³	ASTM D1622	kg/m ³	nominal	100
Druckbelastbarkeit	ASTM D1621-10	MPa	average min-ave min-min	1,93 1,72 1,47
Druckbelastungsmodul	ASTM D1621-10	MPa	average min-ave min-min	90 76 64
Bruchwiderstand	ASTM D1623	MPa	average min-ave min-min	3,08 2,31 2,06
Bruchmodul	ASTM D1623	MPa	average min-ave min-min	169 138 123
Scherfestigkeit	ASTM C273	MPa	average min-ave min-min	1,49 1,43 1,25
Schermodul	ASTM C273	MPa	average min-ave min-min	37 33 29
Scherbruchdehnung	ASTM C273	%	average	25
Standard Formate		mm		950 2050 68