

PVC 200 Hartschaum



Dichte kg/m ³	ASTM D1622	kg/m ³	nominal	200
Druckbelastbarkeit	ASTM D1621-10	MPa	average min-ave min-min	4,84 4,64 4,00
Druckbelastungsmodul	ASTM D1621-10	MPa	average min-ave min-min	212 198 172
Bruchwiderstand	ASTM D1623	MPa	average min-ave min-min	6,61 5,61 5,33
Bruchmodul	ASTM D1623	MPa	average min-ave min-min	415 343 317
Scherfestigkeit	ASTM C273	MPa	average min-ave min-min	3,59 3,23 2,81
Schermodul	ASTM C273	MPa	average min-ave min-min	78 74 65
Scherbruchdehnung	ASTM C273	%	average	41
Standard Formate		mm		750 1600 48