

## Espuma de PVC 40



Densidad kg/m <sup>3</sup>	ASTM D1622	kg/m <sup>3</sup>	nominal	40
Resistencia a la compresión	ASTM D1621-10	MPa	average min-ave min-min	0,51 0,30 0,20
Modulo de compresión	ASTM D1621-10	MPa	average min-ave min-min	24 10 5
Resistencia a la rotura	ASTM D1623	MPa	average min-ave min-min	0,74 0,47 -
Modulo de rotura	ASTM D1623	MPa	average min-ave min-min	74 44 36
Resistencia al corte	ASTM C273	MPa	average min-ave min-min	0,41 0,34 0,25
Modulo de corte	ASTM C273	MPa	average min-ave min-min	13 9 6
Alargamiento de corte a la rotura	ASTM C273	%	average	5
Medidas estandar		mm		1330 2850 84