

PVC 60 Hartschaum



Dichte kg/m ³	ASTM D1622	kg/m ³	nominal	60
Druckbelastbarkeit	ASTM D1621-10	MPa	average min-ave min-min	0,96 0,75 0,61
Druckbelastungsmodul	ASTM D1621-10	MPa	average min-ave min-min	46 31 25
Bruchwiderstand	ASTM D1623	MPa	average min-ave min-min	2,11 1,33 1,19
Bruchmodul	ASTM D1623	MPa	average min-ave min-min	106 75 66
Scherfestigkeit	ASTM C273	MPa	average min-ave min-min	0,77 0,70 0,60
Schermodul	ASTM C273	MPa	average min-ave min-min	21 17 14
Scherbruchdehnung	ASTM C273	%	average	13
Standard Formate		mm		1150 2450 78