

PVC 80 Hartschaum



Dichte kg/m ³	ASTM D1622	kg/m ³	nominal	80
Druckbelastbarkeit	ASTM D1621-10	MPa	average min-ave min-min	1,43 1,22 1,03
Druckbelastungsmodul	ASTM D1621-10	MPa	average min-ave min-min	68 53 44
Bruchwiderstand	ASTM D1623	MPa	average min-ave min-min	2,60 1,82 1,63
Bruchmodul	ASTM D1623	MPa	average min-ave min-min	137 107 94
Scherfestigkeit	ASTM C273	MPa	average min-ave min-min	1,13 1,06 0,92
Schermodul	ASTM C273	MPa	average min-ave min-min	29 25 22
Scherbruchdehnung	ASTM C273	%	average	20
Standard Formate		mm		1020 2180 72